## DELCONCA USA

## Del Conca USA - Technical Characteristics

## **SERIE HET**, ESSENTIAL collection.

ANSI A 137.1 - 2019 Table 10 : Porcelain Tile

Reference		Characteristics	Standard	Required values		DC USA Values:
	Calibrated	Nominal Size	ASTM C499	± 3%		Comply
Dimensional standard		Caliber Range	ASTM C499	± 0.5%	± 0.08 in	Comply
		Warpage Edge	ASTM C485	± 0.5%	± 0.07 in	Comply
		Warpage Diagonal	ASTM C485	± 0.5%	± 0.07 in	Comply
		Wedging	ASTM C502	± 0.5%	± 0.08 in	Comply
	Rectified	Nominal Size	ASTM C499	- 3%	+ 2%	Comply
		Caliber Range	ASTM C499	± 0.25%	± 0.03 in	Comply
		Warpage Edge	ASTM C485	± 0.4%	± 0.05 in	Comply
		Warpage Diagonal	ASTM C485	± 0.4%	± 0.07 in	Comply
		Wedging	ASTM C502	± 0.25%	± 0.03 in	Comply
		Thickness	ASTM C499	± 0.040 in		Comply
		DEEP Abrasion	ASTM C1243	<175mm <sup>3</sup>		~ 40 mm <sup>3</sup>
		Bond Strength	ASTM C482	≥ 50 psi		Comply
ard		Water absorption	ASTM C373	Maximum 0.5%		~ 0.1%
Mechanical Standard		Thermal shock resistance	ASTM C484	Pass		Comply
lical		Chemical resistance	ASTM C650	Declared value		Class E
char		Stain resistance	ASTM C1378	Declared value		Class A
Mee		Breaking Strength	ASTM C648	≥ 275 lbf		Comply
		Resistance to Freeze/Thaw cycling	ASTM C1026	As Reported		Comply
		Scratch Hardness	Mohs	Declared value		Mohs ≥7

## DELCONCA USA

_					
	Fire reaction - floor	EN 13823	Not Required		A1fl class (No reaction)
	Fire reaction - wall	EN 13823	Not Required		A1 class (No reaction)
	VOC	No VOC			
US Require ments	Dynamic coefficient of Friction DCOF	ANSI A326.3- 2021	Wet value ≥	Nat	0.45
			0.42	20MM	0.74

Values reflect an average among test performed in our laboratory according to the standard requirements and/or trough third party laboratory.

Test are performed on actual production, first choice material. Values may vary between single individual production run.

Ceramica del Conca Technical team will be pleased to integrate and answer specific questions.